

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

**FINISH
CODE**

**REVISION
LEVEL**

BRIEF DESCRIPTION:

NE-1 EZINC-OLIVE DRAB

NE

1

REV DATE: 09/04/2007

GENERAL DESCRIPTION

.0002 MIN ELECTROPLATED ZINC & OLIVE DRAB CHROMATE

APPEARANCE

UNIFORM OLIVE DRAB

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 132

WHITE CORROSION: 96

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0002 MAX THICKNESS: .0004
THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

PASRTS TO BE BAKED AT 400 DEGREES F FOR 4 HURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOT, POWDERY FILM. SLOUGHING OFF OF FILM & BLISTERING

EQUIVALENT SPECS

GE F70B3A2 (50-407, 50-1251-2A)

APPROVED SUPPLIERS:

PRINT DATE:
02/05/2008