

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

EZINC-BAKE-CHROMAT-UVWAX

NK

0

REV DATE: 4/1/2007

GENERAL DESCRIPTION

.0002 MIN ELECTROPLATED ZINC, OLIVE DRAB CHROMATE & WAX WITH UV TRACER

APPEARANCE

UNIFORM OLIVE DRAB

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 132

WHITE CORROSION: 96

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0002 MAX THICKNESS: .0004
THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOT, POWDERY FILM. SLOUGHING OFF OF FILM & BLISTERING

EQUIVALENT SPECS

APPROVED SUPPLIERS:

PRINT DATE:
3/19/2007